



RUBBER
MASTERBATCH
RANGE

Prisma Colour is the premier supplier of colours to the rubber compounding industry, working with customers in more than 55 countries across the world.

Our customers choose Prisma Colour because of our superior technical and application knowledge which means we can make any colour to meet any application requirement.

This brochure illustrates our standard range of colours. We also offer a bespoke colour matching service. To find out more contact sales@prismacolour.com and a member of our team will be in touch to talk through your specific requirements.

PRISMA PRODUCTS

PRISMAGUM-G: Granulated Chip

Our standard rubber products in granulated chips for easy dosing. Available in multiple polymer types including; EPR, EPDM, NBR and SBR.

PRISMAGUM-X: Highly Dispersed

Highly dispersed colour masterbatches specifically designed for use in printing blankets.

PRISMAGUM-S: Slab Form

Our standard rubber products in slab form. Available in multiple polymer types including; EPR, EPDM, NBR and SBR.

PRISMAGUM-F: Colour Masterbatch for FKM

Specialty masterbatches designed specifically for use in FKM compounds.

A687 Prismagum Yellow



Pigment CI Number:
Yellow 180
Active Content: **55%**
Lightfastness: **6-7**
Weathering: -
Heat Stability: **280°C**

A689 Prismagum Yellow



Pigment CI Number:
Yellow 13
Active Content: **57%**
Lightfastness: **6-7**
Weathering: -
Heat Stability: **200°C**

A688 Prismagum Yellow



Pigment CI Number:
Yellow 83
Active Content: **50%**
Lightfastness: **6-7**
Weathering: -
Heat Stability: **200°C**

B776 Prismagum Yellow



Pigment CI Number:
Yellow 42
Active Content: **60%**
Lightfastness: **8**
Weathering: **5**
Heat Stability: **180°C**

A686 Prismagum Orange



Pigment CI Number:
Orange 13
Active Content: **57%**
Lightfastness: **5**
Weathering: -
Heat Stability: **200°C**

A012 Prismagum Orange



Pigment CI Number:
Orange 34
Active Content: **45%**
Lightfastness: **6-7**
Weathering: -
Heat Stability: **200°C**

C940 Prismafum Red Oxide

Pigment CI Number:
Red 101
Active Content: **50%**
Lightfastness: **8**
Weathering: **5**
Heat Stability: **>300°C**

J752 Prismafum Red

Pigment CI Number:
Red 254
Active Content: **50%**
Lightfastness: **8**
Weathering: **5**
Heat Stability: **300°C**

J636 Prismafum Red

Pigment CI Number:
Red 48:1
Active Content: **60%**
Lightfastness: **5-6**
Weathering: **-**
Heat Stability: **240°C**

A682 Prismafum Red

Pigment CI Number:
Red 38
Active Content: **57%**
Lightfastness: **6**
Weathering: **-**
Heat Stability: **200°C**

J996 Prismafum Red

Pigment CI Number:
Red 48:3
Active Content: **50%**
Lightfastness: **6-7**
Weathering: **-**
Heat Stability: **240°C**

S220 Prismafum Red

Pigment CI Number:
Red 208
Active Content: **55%**
Lightfastness: **6-7**
Weathering: **-**
Heat Stability: **250°C**

J635 Prismafum Red

Pigment CI Number:
Red 57:1
Active Content: **60%**
Lightfastness: **6-7**
Weathering: **-**
Heat Stability: **260°C**

S751 Prismafum Red

Pigment CI Number:
Red 122
Active Content: **50%**
Lightfastness: **7-8**
Weathering: **4-5**
Heat Stability: **300°C**

P259 Prismafum Violet

Pigment CI Number:
Violet 23
Active Content: **30%**
Lightfastness: **7-8**
Weathering: **4-5**
Heat Stability: **260°C**

Y052 Prismafum Blue

Pigment CI Number:
Blue 60
Active Content: **50%**
Lightfastness: **8**
Weathering: **4-5**
Heat Stability: **280°C**

Y671 Prismafum Blue

Pigment CI Number:
Blend*
Active Content: **45%**
Lightfastness: **7-8**
Weathering: **4-5**
Heat Stability: **300°C**

J678 Prismafum Blue


Pigment CI Number:
Blue 15:1
Active Content: **55%**
Lightfastness: **8**
Weathering: **5**
Heat Stability: **300°C**

J937 Prismafum Blue

Pigment CI Number:
Blue 15:3
Active Content: **55%**
Lightfastness: **8**
Weathering: **5**
Heat Stability: **280°C**

P318 Prismafum Green

Pigment CI Number:
Green 17
Active Content: **65%**
Lightfastness: **8**
Weathering: **5**
Heat Stability: **>300°C**

A680 Prismafum Green


Pigment CI Number:
Green 7
Active Content: **60%**
Lightfastness: **8**
Weathering: **5**
Heat Stability: **280°C**

C644 Prismafum Black

Pigment CI Number:
Black 7
Active Content: **50%**
Lightfastness: **8**
Weathering: **5**
Heat Stability: **>300°C**

*This is a blend of pigment types that provides an equivalent colour to PB60 but at a reduced cost.

NOTE: Masterbatch colours may look different in your rubber compound. If you would like to see any of these mixed into your compound please send us some uncoloured base and we will be happy to compound your chosen colours and return the samples to you. The data shown here is based on our current knowledge and experience. Lightfastness data is provided in the blue wool scale (1-8) and tested according to EN ISO8 77. Weathering data is provided in the grey scale (1-5) and tested according to ISO4 892-2:2013. Pigment performance data should be treated as guide as it may vary in your base compound. Prisma Colour has the capacity to perform these tests on your finished compound. If you would like us to carry out these tests please contact our sales department.



prisma
C O L O U R

Prisma Colour Limited

Thornsett Trading Estate, Birch Vale, New Mills,
Derbyshire, SK22 1AH. United Kingdom

T. +44 (0) 1457 856 505

E. sales@prismacolour.com

www.prismacolour.com



Prisma Colour has one of the widest product portfolios in the colour and additive masterbatch industry

Thermoplastic Colour Masterbatch

Thermoplastic Additives

Rotational Moulding Powders

Thermoplastic Compounds

Rubber Colour Masterbatch

Rubber Additives

Silicone Colourants

Liquid Dispersions

Solvent Dispersions

For more information on all our product types, please visit www.prismacolour.com or contact our sales team on **+44 (0) 1457 856 505**